

PPSU/PB

ポリフェニルスルホン / プラばね
Polyphenylsulfone / Plastic spring



表中の数値は参考値であり保証値ではありません。

事前に使用状態でのテストを推奨します。

- ・ 耐熱性、耐薬品性などの特性は使用条件により変化します。
- ・ 製造ロット間での色のばらつきが発生する可能性があります。
- ・ 在庫サイズ、形状及び使用材料メーカーは予告なく変更することがあります。
- ・ 受注品です。(納期約2~3週間)
- ・ 在庫についてはお問い合わせください。

The values in the table are for reference only and are not guaranteed.

Pre-testing in working conditions is recommended.

- ・ Properties such as heat resistance and chemical resistance vary depending on the conditions of use.
- ・ Color variations may occur between production lots.
- ・ Sizes in stock, shapes and manufacturers of materials used are subject to change without notice.
- ・ This part is production on order(Delivery time 2-3 weeks).
- ・ Please contact us to check the status of inventory.

下記品番は2023年3月をもちまして廃番となりました。
The following part numbers have been discontinued as of March 2023.

・ PPSU/PBC

	Ω(オメガタイプ) OMEGA TYPE
品番/Part number	PPSU/PBO 19.5-24-36L
外径(mm) Outside diameter	24
内径(mm) Inside diameter	19.5
自由長(mm) Free length	36
密着長(mm) Closed length	18
ばね定数(N/mm) Spring rate	1.05
販売単位 Quantity	1



販売単位/1
Quantity/1

品番 Part number	PPSU/PB 1-2-8L	PPSU/PB 4-8-30L	PPSU/PB 4-8-50L	PPSU/PB 5-9-20L	PPSU/PB 5-9-30L	PPSU/PB 5-9-40L	PPSU/PB 5-9-50L	PPSU/PB 6-10-30L	PPSU/PB 6-10-40L	PPSU/PB 6-10-50L	PPSU/PB 6-12-25L	PPSU/PB 7.5-10-17.2L
内径(mm)/Inside diameter	1	4	4	5	5	5	5	6	6	6	6	7.5
外径(mm)/Outside diameter	2	8	8	9	9	9	9	10	10	10	12	10
自由長(mm)/Free length	8	30	50	20	30	40	50	30	40	50	25	17.2
密着長(mm)/Closed length	5	18	30	12	18	24	30	18	24	31	14.5	6.5
ばね定数(N/mm)/Constant of spring	0.34	0.58	0.42	0.61	0.51	0.34	0.31	0.74	0.55	0.64	2.57	0.03



販売単位/1
Quantity/1

品番 Part number	PPSU/PB 8-12-30L	PPSU/PB 8-12-40L	PPSU/PB 8-12-50L	PPSU/PB 20.5-25-36L
内径(mm)/Inside diameter	8	8	8	20.5
外径(mm)/Outside diameter	12	12	12	25
自由長(mm)/Free length	30	40	50	36
密着長(mm)/Closed length	18	24	30	16
ばね定数(N/mm)/Constant of spring	0.25	0.24	0.67	0.11

ORDER ▶ 品番・サイズ・販売単位にてご注文ください。 **RoHS2**
Please order by part number, size, and unit volume increment. compliant